

REMARKS

The specification has been amended to perfect the continuity information. The claims are amended to include the Article 19 amendments to the claims. No new matter has been added. Entry of this preliminary amendment is expressly requested. A clean copy of the Article 19 amendments are attached.

Respectfully submitted,

McDERMOTT WILL & EMERY LLP



Michael E. Fogarty
Registration No. 36,139

600 13th Street, N.W.
Washington, DC 20005-3096
Phone: 202.756.8000 MEF:aph
Facsimile: 202.756.8087
Date: December 28, 2005

**Please recognize our Customer No. 20277
as our correspondence address.**

CLAIMS (amended under PCT Article 19)

1. An alkaline battery comprising a positive electrode, a negative electrode and an alkaline electrolyte,

said positive electrode comprising a positive electrode material mixture containing nickel oxyhydroxide, electrolytic manganese dioxide and a graphite conductive material,

wherein said nickel oxyhydroxide comprises a crystal having a β type structure, said crystal having manganese dissolved therein, and

the amount of said manganese contained in said nickel oxyhydroxide is 0.5 to 10 mol% relative to the total amount of nickel and said manganese contained in said nickel oxyhydroxide.

2. (Amended) An alkaline battery comprising a positive electrode, a negative electrode and an alkaline electrolyte,

said positive electrode comprising a positive electrode material mixture containing nickel oxyhydroxide, electrolytic manganese dioxide and a graphite conductive material,

said nickel oxyhydroxide comprising a crystal having manganese dissolved therein and having a β type structure,

wherein, when a molded article comprising a mixture of said nickel oxyhydroxide and said graphite conductive

material is immersed in an aqueous solution containing 40 wt% KOH and a constant current per gram of said nickel oxyhydroxide of 5 mA is applied to said molded article, the potential of said molded article has a first plateau region ranging from +500 to +100 mV relative to an Hg/HgO electrode and a second plateau region ranging from +100 to -400 mV relative to said Hg/HgO electrode,

the discharge capacity per gram of said nickel oxyhydroxide in said first plateau region is 220 to 250 mAh, and

the discharge capacity per gram of said nickel oxyhydroxide in said second plateau region is 10 to 25 mAh.

3. The alkaline battery in accordance with claim 1, wherein the amount of said nickel oxyhydroxide is 10 to 80 wt% relative to the total amount of said nickel oxyhydroxide and said electrolytic manganese dioxide contained in said positive electrode material mixture, and the amount of said electrolytic manganese dioxide is 20 to 90 wt% relative to said total amount.

4. The alkaline battery in accordance with claim 2, wherein the amount of said nickel oxyhydroxide is 10 to 80 wt% relative to the total amount of said nickel oxyhydroxide and said electrolytic manganese dioxide contained in said positive electrode material mixture, and the amount of said electrolytic manganese dioxide is 20 to 90 wt% relative to said total amount.

5. The alkaline battery in accordance with claim 1, wherein the amount of said graphite conductive material is 3 to 10 wt% relative to the total amount of said nickel oxyhydroxide, said electrolytic manganese dioxide and said graphite conductive material contained in said positive electrode material mixture.

6. The alkaline battery in accordance with claim 2, wherein the amount of said graphite conductive material is 3 to 10 wt% relative to the total amount of said nickel oxyhydroxide, said electrolytic manganese dioxide and said graphite conductive material contained in said positive electrode material mixture.

7. The alkaline battery in accordance with claim 1, wherein said positive electrode material mixture further contains at least one rare earth metal oxide selected from the group consisting of Y_2O_3 , Er_2O_3 , Tm_2O_3 , Yb_2O_3 and Lu_2O_3 , and the amount of said rare earth metal oxide is 0.1 to 2 wt% relative to the total amount of said nickel oxyhydroxide, said electrolytic manganese dioxide, said graphite conductive material and said rare earth metal oxide.

8. The alkaline battery in accordance with claim 2, wherein said positive electrode material mixture further contains at least one rare earth metal oxide selected from the group consisting of Y_2O_3 , Er_2O_3 , Tm_2O_3 , Yb_2O_3 and Lu_2O_3 , the amount of said rare earth metal oxide is 0.1 to 2 wt% relative to the total amount of said nickel oxyhydroxide, said

electrolytic manganese dioxide, said graphite conductive material and said rare earth metal oxide.

Brief Statement under Article 19(1)

Claim 2 has been amended to further limit the nickel oxyhydroxide to nickel oxyhydroxide comprising a crystal having manganese dissolved therein and having a β type structure.